
General purpose hoses



VERSITEC

Material: Half transparent silicone
Hardness: 57° Shore (A)
Density: 1.15 g/cm^3
Working temp.: From -50°C up to +200°C (with peaks up to +220°C)

Hose made of peroxide cured silicone. Resistant to UV radiation, oxygen and ozone. Widely used in industry and household appliances. Sterilization with steam, ethylene oxide or radiation. Conforms to FDA and BfR standards.

code	I.D. [mm]	O.D. [mm]	wall thickness [mm]	working pressure [bar]	bending radius [mm]	standard length [m]
VE-761800	0.5	2.5	1	1.3	1	50
VE-761802	1	3	1	1.1	2	50
VE-761804	1.5	3	0.75	0.72	4	50
VE-761806	2	4	1	0.6	7	50
VE-761807	2	5.5	1.75	0.81	3	50
VE-761809	2	6	2	0.9	3	50
VE-761812	3	5	1	0.55	8	50
VE-761814	3	6	1.5	0.64	7	50
VE-761816	3	7	2	0.75	5	50
VE-761819	4	6	1	0.4	15	50
VE-761821	4	7	1.5	0.54	10	25
VE-761823	4	8	2	0.5	8	25
VE-761825	4	10	3	0.75	6	25
VE-761828	5	7	1	0.4	25	25
VE-761830	5	8	1.5	0.45	16	25
VE-761832	5	9	2	0.6	14	25
VE-761834	5	10	2.5	0.64	11	25
VE-761837	6	8	1	0.3	36	25
VE-761839	6	9	1.5	0.37	26	25
VE-761841	6	10	2	0.47	19	25
VE-761843	6	12	3	0.64	12	25
VE-761846	7	10	1.5	0.31	32	25
VE-761848	7	11	2	0.39	23	25
VE-761850	7	12	2.5	0.51	18	25
VE-761852	7	13	3	0.55	15	25
VE-761855	8	11	1.5	0.31	35	25
VE-761857	8	12	2	0.35	28	25
VE-761859	8	14	3	0.5	18	25
VE-761860	8	16	4	0.61	14	25
VE-761862	9	13	2	0.37	39	25
VE-761864	10	14	2	0.36	46	25
VE-761866	10	16	3	0.45	30	25
VE-761868	10	18	4	0.5	26	25
VE-761871	12	17	2.5	0.28	47	25
VE-761874	15	21	3	0.31	70	25
VE-761877	18	24	3	0.26	87	10
VE-761880	20	27	3.5	0.29	102	10
VE-761883	25	35	5	0.28	111	10
VE-761886	30	40	5	0.26	204	10
VE-761888	40	50	5	0.25	270	10